

**Product Data Sheet** 

## **Castrol Hyspin AWS Range**

Anti-wear hydraulic oil

### **Description**

Castrol Hyspin $^{\text{\tiny{TM}}}$  AWS hydraulic oil range is based upon highly refined mineral oil enhanced with a stabilised zinc additive system.

### **Application**

Hyspin AWS has been specially formulated to provide good anti-wear and thermal stability performance using provenadditive technology. The careful blend of additives with a high quality base stock ensures that Hyspin AWS has excellent hydrolytic and oxidative stability while exhibiting a minimal tendency to produce sludge and deposits. In addition, Hyspin AWS provides corrosion protection to ferrous and yellow metal components found within a hydraulic system.

This range is designed for use in industrial hydraulic systems which require anti-wear protection such as lightly loaded gears, variable speed units and bearings. The Hyspin AWS range is compatible with the most commonly used nitrile, silicone and fluropolymer seal materials..

Hyspin AWS is classified as follows: DIN 51502 classification - HLP ISO 6743/4 - Hydraulic Oils Type HM

Hyspin AWS (for appropriate viscosity grade) is approved by: Parker Hannifin (Denison) HF0, HF1 & HF2 Eaton E-FDGN-TB002-E

Hyspin AWS grades meet the requirements (for appropriate viscosity grade) of: DIN 51524 Part 2
Fives Cincinnati P68, P69 & P70
ASTM D6158 HM
ISO 11158 HM
US Steel 126
GB 11118.1 L-HM (General and High Pressure)

## **Advantages**

Hyspin AWS has the following advantages when compared to conventional hydraulic oils:

- Good thermal and oxidative stability. Oxidative stability reduces deposit formation, resulting in a cleaner system. This can extend the machinery's operating life.
- Excellent anti-wear performance increases wear protection, which can help reduce downtime caused by unscheduled maintenance.
- Good filterability characteristics, including in the presence of water, enables cost savings to be made from increased filter life and reduced maintenance.
- Excellent water separation and hydrolytic stability, measured by industry standard testing. This increases equipment reliability, helping to prolong the lubricant's life and reduce downtime.

# **Typical Characteristics**

| Name  | Method                       | Units                    | AWS<br>10   | AWS<br>15   | AWS<br>22   | AWS<br>32   | AWS<br>46   | AWS<br>68   | AWS<br>100  | AWS<br>150  | AWS<br>220  |
|---|------------------------------|--------------------------|-------------|-------------|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| ISO Viscosity<br>Grade                          | -                            | -                        | 10          | 15          | 22          | 32          | 46          | 68          | 100         | 150         | 220         |
| Density @ 15°C /<br>59°F                        | ISO 12185 /<br>ASTM<br>D4052 | kg/m³                    | 890         | 870         | 870         | 880         | 880         | 880         | 890         | 890         | 890         |
| Kinematic<br>Viscosity @ 40°C /<br>104°F        | ISO 3104 /<br>ASTM D445      | mm²/s                    | 10          | 15          | 22          | 32          | 46          | 68          | 100         | 150         | 220         |
| Kinematic<br>Viscosity @ 100°C<br>/ 212°F       | ISO 3104 /<br>ASTM D445      | mm²/s                    | 2.4         | 3.2         | 4.3         | 5.3         | 6.7         | 8.6         | 11.1        | 14.5        | 18.7        |
| Viscosity Index                                 | ISO 2909 /<br>ASTM<br>D2270  | -                        | -           | -           | >95         | >95         | >95         | >95         | >95         | >95         | >95         |
| Pour Point                                      | ISO 3016 /<br>ASTM D97       | °C/°F                    | -36/<br>-33 | -33/<br>-27 | -27/<br>-17 | -27/<br>-17 | -24/<br>-11 | -21/<br>-6  | -18/<br>0   | -15/<br>5   | -12/<br>10  |
| Foam Sequence I - tendency / stability          | ISO 6247 /<br>ASTM D892      | ml/ml                    | 10/0        | 10/0        | 10/0        | 10/0        | 10/0        | 10/0        | 10/0        | 10/0        | 10/0        |
| Flash Point - open cup method                   | ISO 2592 /<br>ASTM D92       | °C/°F                    | 170/<br>338 | 195/<br>383 | 205/<br>401 | 210/<br>410 | 215/<br>419 | 225/<br>437 | 225/<br>437 | 230/<br>446 | 255/<br>491 |
| Flash Point -<br>closed cup<br>method           | ISO 2719 /<br>ASTM D93       | °C/°F                    | 145/<br>293 | 160/<br>320 | 170/<br>338 | 200/<br>392 | 200/<br>392 | 220/<br>428 | 220/<br>428 | 220/<br>428 | 230/<br>446 |
| Water Separation<br>@ 54°C / 129°F<br>(40/37/3) | ISO 6614 /<br>ASTM<br>D1401  | min                      | 5           | 10          | 10          | 15          | 15          | 15          | -           | -           | -           |
| Water Separation<br>@ 82°C / 180°F<br>(40/37/3) | ISO 6614 /<br>ASTM<br>D1401  | min                      | -           | -           | -           | -           | -           | -           | 15          | 20          | 20          |
| Air Release @<br>50°C / 122°F                   | ISO 9120 /<br>ASTM<br>D3427  | min                      | 4           | 4           | 4           | 4           | 8           | 8           | 12          | 18          | 29          |
| FZG Gear Scuffing<br>test - A/8.3/90            | ISO<br>14635-1               | Failure<br>Load<br>Stage | -           | -           | -           | 11          | 12          | 12          | 12          | 12          | 12          |
| Rust test -<br>distilled water (24<br>hrs)      | ISO 7120 /<br>ASTM<br>D665A  | -                        | Pass        |
| Rust test -<br>synthetic<br>seawater (24 hrs)   | ISO 7120 /<br>ASTM<br>D665B  | -                        | Pass        |
| Oxidation Stability<br>- TOST                   | ISO 4263-1<br>/ ASTM<br>D943 | hours                    | -           | -           | -           | >2500       | >2500       | >2500       | -           | -           | -           |

Subject to usual manufacturing tolerances.

#### **Storage**

All packages should be stored under cover. Where outside storage is unavoidable drums should be laid horizontally to avoid the possible ingress of water and the obliteration of drum markings. Products should not be stored above 60°C, exposed to hot sun or freezing conditions.

Castrol Hyspin AWS Range 08 Sep 2023

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol BP Petco, 9th Floor – Times Square Building, 57-69F Dong Khoi Street, District 1, Ho Chi Minh City, Vietnam Tel: 84-28-38219596 / 38219153 Fax: 84-28-38219603 / 38219152 www.castrol.com